

vebrocrete ESD MF (pf)

Medium duty, easily-applied, self smoothing, PU concrete for areas where ESD protection is critical.

why choose vebrocrete ESD MF?

-  High temperature resistance up to 70°C
-  Excellent resistance to corrosive foodstuffs & aggressive cleaning solvents
-  Excellent cleanability & seamless hygienic finish
-  Food-safe; solvent-free, odourless, non-tainting & non-dusting
-  Complies with HACCP food safety management guidelines
-  Free from phthalates and other LBC Red List 'worst-in-class' materials



system design & typical properties

1 Primer	vebro EP Primer or vebrocrete PU MF (pf) (unpigmented)	0.25 kg/m ² 1.90 kg/m ² (adds 1.0 mm)
2 Copper Tape		
3 ESD Primer	vebro ESD Primer	0.10 kg/m ²
4 Topping	vebrocrete PU ESD MF (pf)	5.70 kg/m ²

Thickness	3.0 – 4.0 mm
FeRFA Type <small>BS 8204-6</small>	Type 7
Temperature Resistance	5 – 70°C at 3.0 mm
Fire Resistance <small>EN 1350-1</small>	B _f S1
Conductivity <small>EN 61340-4-1</small>	<10 ⁹ Ω
Co-efficient of Thermal Expansion <small>ASTM C531</small>	5.8 × 10 ⁻⁵ / °C
Slip Resistance <small>TRLL Pendulum Slip Test / DIN 51130</small>	Dry >70, Wet >21 / R9
Abrasion Resistance <small>EN 13892-4 / BS 8204-2</small>	AR 0.5 / Special Class
Shore D Hardness	80 after 28 days
Compressive Strength <small>EN 196-1 / ASTM C109</small>	50 N/mm ²
Speed of Cure (at 20°C)	Light Foot Traffic – 12 hours Full Chemical Cure – 7 days

For a full technical profile, please refer to the data sheet for each product in the system design.

contact the vebro team

w: vebropolymers.com | e: asia@vebropolymers.com | t: +60 3 5871 2968* / 2969† | f: +60 3 5871 2970

Please note, the applied colours may differ from the examples shown. vebrocrete systems may exhibit a yellowing effect over time resulting from thermal, UV or chemical exposure. This will be more pronounced on light grey or blue shades. *Colours marked with an asterisk will incur an additional supplement. The typical physical properties given above are derived from testing in a controlled laboratory environment at 20°C. Results derived from testing field applied samples may vary dependent upon site conditions. The slip resistance figures given above are affected by application techniques and prevailing site conditions. Slip resistance can reduce over time due to poor maintenance, general wear or surface contaminants. Good housekeeping practices should be observed.

