

vebrodeck PU ID



A polyurethane-based car park deck coating system designed for interior parking decks of multi-storey parking decks.

why choose vebrodeck PU ID?



Suited to internal parking decks, ramps & turning circles











Economic deck coating system



Resistant to foot & wheeled traffic



Resistant to oils, petrol & other chemicals

		
Light Grey (RAL 7035)	Silver Grey (RAL 7001)	Slate Grey (RAL 7015)
		
Ivory (RAL 1014)	Light Blue (RAL 5012)	Traffic Blue (RAL 5017)
		
Coral Red (RAL 3016)	Emerald Green (RAL 6001)	

system design & typical properties

1 Primer	vebrodeck PU BC	0.70 – 0.80 kg/m ²
2 Scatter	30 – 80s mesh sand	2.00 kg/m ²
3 Coating	vebrodeck PU TC	0.65 – 0.70 kg/m ²

Thickness	1.5 – 2.0 mm
Speed of Cure (at 25°C)	Light Foot Traffic – 24 hours Full Chemical Cure – 7 days
Abrasion Resistance <small>EN 13892-4 / BS 8204-2</small>	AR 0.5 / Special Class
Abrasion Resistance <small>EN ISO 5470-1</small>	1.9 mg / 1000 U (≤ 3.000)
Impact Resistance <small>EN ISO 6772-2</small>	4 Nm (no cracks)
Chemical Resistance	Resistant to a very wide range of chemicals. For a full chemical resistance breakdown contact our Technical Services team.
Adhesion <small>EN ISO 4624</small>	>1.5 N/mm ² (concrete failure)
Fire Resistance <small>EN ISO 13501</small>	B _f -s1
Water Vapour Permeability <small>EN ISO 7783-2</small>	Class III >200 m
Water Absorption <small>EN 1062-3</small>	<0.01 kg/m ²

For a full technical profile, please refer to the data sheet for each product in the system design.

contact the vebro team

w: vebropolymers.com | e: india@vebropolymers.com | t: +91-44-46003465

Please note, the applied colours may differ from the examples shown. The typical physical properties given above are derived from testing in a controlled laboratory environment at 20°C. Results derived from testing field applied samples may vary dependent upon site conditions. The slip resistance figures given above are affected by application techniques and prevailing site conditions. Slip resistance can reduce over time due to poor maintenance, general wear or surface contaminants. Good housekeeping practices should be observed.

